

102001-200

PERFORATED PROPELLANT AND
METHOD OF MANUFACTURING SAME

This application claims the benefit of Provisional
Application Serial No. 60/121,208 filed on February 23, 1999.

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a propellant composition made from a lacquer and processed to form hollow propellant grains that are useful for ammunition rounds. More particularly, the invention is directed to a low viscosity lacquer that is continuously processed by extrusion to form hollow hardened propellant grains in a liquid slurry.

2. Description of Related Art

Perforated propellant grains are generally produced by extruding lacquers having between 0 and 20% by weight of solvent. This method of production requires a pressure in the range of between about 1000 and 5000 psi to extrude the lacquer through an extrusion die assembly, and requires large quantities

of energy and expensive equipment. The following U.S. Patents are representative of the state of the art.

United States Patent No. 5,821,449 entitled, "Propellant grain geometry for controlling ullage and increasing flame permeability" that issued on October 13, 1998 discloses hollow grain propellants for use in lightweight training rounds.

United States Patent No. 4,841,863 entitled, "Saboted, light armour penetrator round with improved powder mix" that issued on June 27, 1989 discloses propellant in the form of spheroidal (substantially spherical) powders and recites that a batch process for the manufacture of spherical powders is disclosed in United States patent number 2,027,114 and a continuous process in United States patent number 3,679,782.

United States Patent Number 5,524,544 entitled, "Nitrocellulose propellant containing a cellulosic burn rate modifier" that issued on June 11, 1996 and United States Patent Number 5,510,062 entitled, "Method of producing a nitrocellulose propellant containing a cellulosic burn rate modifier infiltrated therein that issued on April 23, 1996 disclose a solvent process for the manufacture of propellant grains where a burn rate deterrent is gradationally dispersed within the propellant with the greatest concentration of deterrent at the particulate periphery.

United States patent numbers 2,027,114; 3,679,782;
4,841,863; 5,510,062; 5,524,544 and 5,821,449 are all
incorporated by reference in their entireties herein.

Accordingly, what is needed in the art is a lacquer
composition and method of manufacturing that efficiently
produces perforated propellant grains in a safe and economical
manner, and at a lower extrusion pressure than presently used.
The present invention is believed to be an answer to that need.

SUMMARY OF THE INVENTION

In one aspect, the present invention is directed to a
propellant composition made from a lacquer, the lacquer
comprising: (a) from about 15 to about 70 wt% of an organic
solvent; (b) from about 0.1 to about 2.5 wt% of a stabilizer;
(c) optionally, from about 0% to about 40 wt% of an energetic
plasticizer; (d) optionally, from about 0 to about 10 wt% of a
nonenergetic plasticizer; (e) optionally, from about 0 to about
10 wt% water; (f) optionally, from about 0 to about 15 wt% of
additional additives; and balance being nitrocellulose; all
weight percents based on the total weight of the composition,
and wherein the lacquer has a viscosity of less than 10 million
centipoise when processed.

In another aspect, the present invention is directed to a
propellant composition made from a lacquer, the lacquer

consisting essentially of: (a) from about 30 to about 65 wt% of an organic solvent selected from the group consisting of ethyl acetate, ether, acetone, and combinations thereof; (b) from about 0.25 to about 1.5 wt% of a stabilizer selected from the group consisting of diphenylamine, ethyl centralite, diethyldiphenylurea, 2-nitrodiphenylamine, N-nitrosodiphenylamine, and combinations thereof; (c) optionally, from about 5% to about 25 wt% of nitroglycerin as an energetic plasticizer; (d) optionally, from about 0 to about 3 wt% of a nonenergetic plasticizer selected from the group consisting of dibutylphthalate, adipate esters, and combinations thereof; (e) optionally, from about from about 0 to about 4 wt% water; (f) optionally, from about 0 to about 15 wt% of additional additives selected from the group consisting of lubricants; coolants; barrel wear additives; flash suppressants; decoppering agents; energetic solids, and combinations thereof; and balance being nitrocellulose; wherein all weight percents are based on the total weight of the composition, and wherein the lacquer has a viscosity of between 1 million and 3 million centipoise.

In another aspect, the present invention is directed to a method for manufacturing perforated propellant grains, comprising the steps of: extruding a propellant lacquer through an extrusion die assembly to form one or more propellant lacquer strands, the extrusion die assembly having a plurality of holes,

each of the holes having at least one pin tip positioned therein, the propellant lacquer comprising: (a) from about 15 to about 70 wt% of an organic solvent; (b) from about 0.1 to about 2.5 wt% of a stabilizer; (c) optionally, from about 0% to about 40 wt% of an energetic plasticizer; (d) optionally, from about 0 to about 10 wt% of a nonenergetic plasticizer; (e) optionally, from about 0 to about 10 wt% water; (f) optionally, from about 0 to about 15 wt% of additional additives; and balance being nitrocellulose; all weight percents based on the total weight of the composition, and wherein the lacquer has an extrusion viscosity of less than 10 million centipoise; cutting the propellant lacquer strand to a desired dimension to form perforated propellant grains; suspending the perforated propellant grains in a water based liquor; removing the organic solvent and water from the perforated propellant grains; and hardening the perforated propellant grains.

In another aspect, the present invention is directed to a propellant grain having outwardly extending ridges.

In another aspect, the present invention is directed to a propellant grain having an ellipsoidal cross section.

These and other aspects will be more fully understood from the following detailed description of the invention.

DESCRIPTION OF THE DRAWINGS

The invention will be more fully understood from the following detailed description taken in conjunction with the accompanying drawings in which:

5 Fig. 1A shows a hollow, tubular portion of the propellant grains of the invention having a single internal perforation;

 Fig. 1B shows the hollow, tubular portion of Fig. 1A in a flattened state;

10 Fig. 2A shows an alternative embodiment of the propellant grains of the invention having a plurality of internal perforations;

15 Fig. 2B shows the alternative embodiment of Fig. 2A in a flattened state; and

20 Fig. 3 shows another alternative embodiment of the propellant grains of the invention having outwardly extending ridges.

DETAILED DESCRIPTION OF THE INVENTION

It has now been found that perforated propellant grains may be manufactured continuously from a specific lacquer composition in a safe, cost-effective, and efficient manner. The continuous preparation of a perforated propellant produces a strand having a generally cylindrical shape with one or more inner concentric hollow cylinders (termed perforations) arranged parallel to the

longitudinal axis of the strand. The produced strands may be cut to desired sizes, may be flattened to form ellipsoid shapes, or may be formed to specific configurations (e.g., with outwardly extending ridges). The cut strands (grains) are made from a composition that requires less pressure to extrude during the manufacturing process, thereby considerably reducing energy and equipment costs.

As defined herein, the term "perforation" refers to a tubular space (hollow cylinder) oriented parallel to the longitudinal axis of the strand or grain.

As indicated above, the propellant of the present invention is made from a lacquer comprising (a) an organic solvent; (b) a stabilizer; (c) optionally, an energetic plasticizer; (d) optionally, a nonenergetic plasticizer; (e) optionally, water; and (f) optionally, additional additives; and the balance being nitrocellulose. Each of these components is discussed in detail below.

Solvents that are useful in the composition and method of the present invention include ethyl acetate, ether, acetone, and combinations thereof. A preferred solvent is ethyl acetate. Preferably, the amount of solvent used in the composition of the invention ranges from about 15 to about 70 wt%, and more preferably from about 30 to about 65 wt%, based on the total weight of the composition.

The lacquer composition of the invention also includes one or more stabilizers. Examples of suitable stabilizers include diphenylamine, ethyl centralite, diethyldiphenylurea, 2-nitrodiphenylamine, N-nitrosodiphenylamine, and combinations thereof. Useful amounts of the stabilizers in the composition of the present invention generally range from 0.1 wt% to about 2.5 wt%, and more preferably from about 0.25 wt% to about 1.5 wt%, based on the total weight of the composition.

The balance of the lacquer composition of the invention is nitrocellulose. The nitrocellulose used in the present invention may be in any form. However, in a preferred embodiment, the nitrocellulose is completely dissolved in one or more solvents.

Optionally, the lacquer composition of the invention includes an energetic plasticizer such as nitroglycerin, ethylene glycol esters, methylene glycols, glycol esters, formyl acetal (bis(2,2-dinitropropyl)formal acetal) and combinations thereof. If such an energetic plasticizer is included in the composition, a useful working range is from about 0% to about 40 wt%, and more preferably from about 5 to about 25 wt%, based on the total weight of the composition.

Optionally, the lacquer composition of the invention also includes a nonenergetic plasticizer such as dibutylphthalate, adipate esters, and combinations thereof. A preferred

nonenergetic plasticizer is DBP (dibutylphthalate). Generally, the nonenergetic plasticizer component comprises from about 0 to about 10 wt%, and more preferably from about 0 wt% to about 3 wt%, based on the total weight of the composition.

5 The lacquer composition of the invention may also include optional additives, including lubricants, such as graphite; coolants, such as magnesium carbonate; barrel wear additives, such as tin dioxide, titanium dioxide, calcium bicarbonate, and the like; flash suppressants, such as potassium salts; decoppering agents, such as bismuth and tin dioxides; and energetic solids known in the art, such as RDX, HMX, CL20, nitroguanidine, and the like.

10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995
1000
1005
1010
1015
1020
1025
1030
1035
1040
1045
1050
1055
1060
1065
1070
1075
1080
1085
1090
1095
1100
1105
1110
1115
1120
1125
1130
1135
1140
1145
1150
1155
1160
1165
1170
1175
1180
1185
1190
1195
1200
1205
1210
1215
1220
1225
1230
1235
1240
1245
1250
1255
1260
1265
1270
1275
1280
1285
1290
1295
1300
1305
1310
1315
1320
1325
1330
1335
1340
1345
1350
1355
1360
1365
1370
1375
1380
1385
1390
1395
1400
1405
1410
1415
1420
1425
1430
1435
1440
1445
1450
1455
1460
1465
1470
1475
1480
1485
1490
1495
1500
1505
1510
1515
1520
1525
1530
1535
1540
1545
1550
1555
1560
1565
1570
1575
1580
1585
1590
1595
1600
1605
1610
1615
1620
1625
1630
1635
1640
1645
1650
1655
1660
1665
1670
1675
1680
1685
1690
1695
1700
1705
1710
1715
1720
1725
1730
1735
1740
1745
1750
1755
1760
1765
1770
1775
1780
1785
1790
1795
1800
1805
1810
1815
1820
1825
1830
1835
1840
1845
1850
1855
1860
1865
1870
1875
1880
1885
1890
1895
1900
1905
1910
1915
1920
1925
1930
1935
1940
1945
1950
1955
1960
1965
1970
1975
1980
1985
1990
1995
2000
2005
2010
2015
2020
2025
2030
2035
2040
2045
2050
2055
2060
2065
2070
2075
2080
2085
2090
2095
2100
2105
2110
2115
2120
2125
2130
2135
2140
2145
2150
2155
2160
2165
2170
2175
2180
2185
2190
2195
2200
2205
2210
2215
2220
2225
2230
2235
2240
2245
2250
2255
2260
2265
2270
2275
2280
2285
2290
2295
2300
2305
2310
2315
2320
2325
2330
2335
2340
2345
2350
2355
2360
2365
2370
2375
2380
2385
2390
2395
2400
2405
2410
2415
2420
2425
2430
2435
2440
2445
2450
2455
2460
2465
2470
2475
2480
2485
2490
2495
2500
2505
2510
2515
2520
2525
2530
2535
2540
2545
2550
2555
2560
2565
2570
2575
2580
2585
2590
2595
2600
2605
2610
2615
2620
2625
2630
2635
2640
2645
2650
2655
2660
2665
2670
2675
2680
2685
2690
2695
2700
2705
2710
2715
2720
2725
2730
2735
2740
2745
2750
2755
2760
2765
2770
2775
2780
2785
2790
2795
2800
2805
2810
2815
2820
2825
2830
2835
2840
2845
2850
2855
2860
2865
2870
2875
2880
2885
2890
2895
2900
2905
2910
2915
2920
2925
2930
2935
2940
2945
2950
2955
2960
2965
2970
2975
2980
2985
2990
2995
3000
3005
3010
3015
3020
3025
3030
3035
3040
3045
3050
3055
3060
3065
3070
3075
3080
3085
3090
3095
3100
3105
3110
3115
3120
3125
3130
3135
3140
3145
3150
3155
3160
3165
3170
3175
3180
3185
3190
3195
3200
3205
3210
3215
3220
3225
3230
3235
3240
3245
3250
3255
3260
3265
3270
3275
3280
3285
3290
3295
3300
3305
3310
3315
3320
3325
3330
3335
3340
3345
3350
3355
3360
3365
3370
3375
3380
3385
3390
3395
3400
3405
3410
3415
3420
3425
3430
3435
3440
3445
3450
3455
3460
3465
3470
3475
3480
3485
3490
3495
3500
3505
3510
3515
3520
3525
3530
3535
3540
3545
3550
3555
3560
3565
3570
3575
3580
3585
3590
3595
3600
3605
3610
3615
3620
3625
3630
3635
3640
3645
3650
3655
3660
3665
3670
3675
3680
3685
3690
3695
3700
3705
3710
3715
3720
3725
3730
3735
3740
3745
3750
3755
3760
3765
3770
3775
3780
3785
3790
3795
3800
3805
3810
3815
3820
3825
3830
3835
3840
3845
3850
3855
3860
3865
3870
3875
3880
3885
3890
3895
3900
3905
3910
3915
3920
3925
3930
3935
3940
3945
3950
3955
3960
3965
3970
3975
3980
3985
3990
3995
4000
4005
4010
4015
4020
4025
4030
4035
4040
4045
4050
4055
4060
4065
4070
4075
4080
4085
4090
4095
4100
4105
4110
4115
4120
4125
4130
4135
4140
4145
4150
4155
4160
4165
4170
4175
4180
4185
4190
4195
4200
4205
4210
4215
4220
4225
4230
4235
4240
4245
4250
4255
4260
4265
4270
4275
4280
4285
4290
4295
4300
4305
4310
4315
4320
4325
4330
4335
4340
4345
4350
4355
4360
4365
4370
4375
4380
4385
4390
4395
4400
4405
4410
4415
4420
4425
4430
4435
4440
4445
4450
4455
4460
4465
4470
4475
4480
4485
4490
4495
4500
4505
4510
4515
4520
4525
4530
4535
4540
4545
4550
4555
4560
4565
4570
4575
4580
4585
4590
4595
4600
4605
4610
4615
4620
4625
4630
4635
4640
4645
4650
4655
4660
4665
4670
4675
4680
4685
4690
4695
4700
4705
4710
4715
4720
4725
4730
4735
4740
4745
4750
4755
4760
4765
4770
4775
4780
4785
4790
4795
4800
4805
4810
4815
4820
4825
4830
4835
4840
4845
4850
4855
4860
4865
4870
4875
4880
4885
4890
4895
4900
4905
4910
4915
4920
4925
4930
4935
4940
4945
4950
4955
4960
4965
4970
4975
4980
4985
4990
4995
5000
5005
5010
5015
5020
5025
5030
5035
5040
5045
5050
5055
5060
5065
5070
5075
5080
5085
5090
5095
5100
5105
5110
5115
5120
5125
5130
5135
5140
5145
5150
5155
5160
5165
5170
5175
5180
5185
5190
5195
5200
5205
5210
5215
5220
5225
5230
5235
5240
5245
5250
5255
5260
5265
5270
5275
5280
5285
5290
5295
5300
5305
5310
5315
5320
5325
5330
5335
5340
5345
5350
5355
5360
5365
5370
5375
5380
5385
5390
5395
5400
5405
5410
5415
5420
5425
5430
5435
5440
5445
5450
5455
5460
5465
5470
5475
5480
5485
5490
5495
5500
5505
5510
5515
5520
5525
5530
5535
5540
5545
5550
5555
5560
5565
5570
5575
5580
5585
5590
5595
5600
5605
5610
5615
5620
5625
5630
5635
5640
5645
5650
5655
5660
5665
5670
5675
5680
5685
5690
5695
5700
5705
5710
5715
5720
5725
5730
5735
5740
5745
5750
5755
5760
5765
5770
5775
5780
5785
5790
5795
5800
5805
5810
5815
5820
5825
5830
5835
5840
5845
5850
5855
5860
5865
5870
5875
5880
5885
5890
5895
5900
5905
5910
5915
5920
5925
5930
5935
5940
5945
5950
5955
5960
5965
5970
5975
5980
5985
5990
5995
6000
6005
6010
6015
6020
6025
6030
6035
6040
6045
6050
6055
6060
6065
6070
6075
6080
6085
6090
6095
6100
6105
6110
6115
6120
6125
6130
6135
6140
6145
6150
6155
6160
6165
6170
6175
6180
6185
6190
6195
6200
6205
6210
6215
6220
6225
6230
6235
6240
6245
6250
6255
6260
6265
6270
6275
6280
6285
6290
6295
6300
6305
6310
6315
6320
6325
6330
6335
6340
6345
6350
6355
6360
6365
6370
6375
6380
6385
6390
6395
6400
6405
6410
6415
6420
6425
6430
6435
6440
6445
6450
6455
6460
6465
6470
6475
6480
6485
6490
6495
6500
6505
6510
6515
6520
6525
6530
6535
6540
6545
6550
6555
6560
6565
6570
6575
6580
6585
6590
6595
6600
6605
6610
6615
6620
6625
6630
6635
6640
6645
6650
6655
6660
6665
6670
6675
6680
6685
6690
6695
6700
6705
6710
6715
6720
6725
6730
6735
6740
6745
6750
6755
6760
6765
6770
6775
6780
6785
6790
6795
6800
6805
6810
6815
6820
6825
6830
6835
6840
6845
6850
6855
6860
6865
6870
6875
6880
6885
6890
6895
6900
6905
6910
6915
6920
6925
6930
6935
6940
6945
6950
6955
6960
6965
6970
6975
6980
6985
6990
6995
7000
7005
7010
7015
7020
7025
7030
7035
7040
7045
7050
7055
7060
7065
7070
7075
7080
7085
7090
7095
7100
7105
7110
7115
7120
7125
7130
7135
7140
7145
7150
7155
7160
7165
7170
7175
7180
7185
7190
7195
7200
7205
7210
7215
7220
7225
7230
7235
7240
7245
7250
7255
7260
7265
7270
7275
7280
7285
7290
7295
7300
7305
7310
7315
7320
7325
7330
7335
7340
7345
7350
7355
7360
7365
7370
7375
7380
7385
7390
7395
7400
7405
7410
7415
7420
7425
7430
7435
7440
7445
7450
7455
7460
7465
7470
7475
7480
7485
7490
7495
7500
7505
7510
7515
7520
7525
7530
7535
7540
7545
7550
7555
7560
7565
7570
7575
7580
7585
7590
7595
7600
7605
7610
7615
7620
7625
7630
7635
7640
7645
7650
7655
7660
7665
7670
7675
7680
7685
7690
7695
7700
7705
7710
7715
7720
7725
7730
7735
7740
7745
7750
7755
7760
7765
7770
7775
7780
7785
7790
7795
7800
7805
7810
7815
7820
7825
7830
7835
7840
7845
7850
7855
7860
7865
7870
7875
7880
7885
7890
7895
7900
7905
7910
7915
7920
7925
7930
7935
7940
7945
7950
7955
7960
7965
7970
7975
7980
7985
7990
7995
8000
8005
8010
8015
8020
8025
8030
8035
8040
8045
8050
8055
8060
8065
8070
8075
8080
8085
8090
8095
8100
8105
8110
8115
8120
8125
8130
8135
8140
8145
8150
8155
8160
8165
8170
8175
8180
8185
8190
8195
8200
8205
8210
8215
8220
8225
8230
8235
8240
8245
8250
8255
8260
8265
8270
8275
8280
8285
8290
8295
8300
8305
8310
8315
8320
8325
8330
8335
8340
8345
8350
8355
8360
8365
8370
8375
8380
8385
8390
8395
8400
8405
8410
8415
8420
8425
8430
8435
8440
8445
8450
8455
8460
8465
8470
8475
8480
8485
8490
8495
8500
8505
8510
8515
8520
8525
8530
8535
8540
8545
8550
8555
8560
8565
8570
8575
8580
8585
8590
8595
8600
8605
8610
8615
8620
8625
8630
8635
8640
8645
8650
8655
8660
8665
8670
8675
8680
8685
8690
8695
8700
8705
8710
8715
8720
8725
8730
8735
8740
8745
8750
8755
8760
8765
8770
8775
8780
8785
8790
8795
8800
8805
8810
8815
8820
8825
8830
8835
8840
8845
8850
8855
8860
8865
8870
8875
8880
8885
8890
8895
8900
8905
8910
8915
8920
8925
8930
8935
8940
8945
8950
8955
8960
8965
8970
8975
8980
8985
8990
8995
9000
9005
9010
9015
9020
9025
9030
9035
9040
9045
9050
9055
9060
9065
9070
9075
9080
9085
9090
9095
9100
9105
9110
9115
9120
9125
9130
9135
9140
9145
9150
9155
9160
9165
9170
9175
9180
9185
9190
9195
9200
9205
9210
9215
9220
9225
9230
9235
9240
9245
9250
9255
9260
9265
9270
9275
9280
9285
9290
9295
9300
9305
9310
9315
9320
9325
9330
9335
9340
9345
9350
9355
9360
9365
9370
9375
9380
9385
9390
9395
9400
9405
9410
9415
9420
9425
9430
9435
9440
9445
9450
9455
9460
9465
9470
9475
9480
9485
9490
9495
9500
9505
9510
9515
9520
9525
9530
9535
9540
9545
9550
9555
9560
9565
9570
9575
9580
9585
9590
9595
9600
9605
9610
9615
9620
9625
9630
9635
9640
9645
9650
9655
9660
9665
9670
9675
9680
9685
9690
9695
9700
9705
9710
9715
9720
9725
9730
9735
9740
9745
9750
9755
9760
9765
9770
9775
9780
9785
9790
9795
9800
9805
9810
9815
9820
9825
9830
9835
9840
9845
9850
9855
9860
9865
9870
9875
9880
9885
9890
9895
9900
9905
9910
9915
9920
9925
9930
9935
9940
9945
9950
9955
9960
9965
9970
9975
9980
9985
9990
9995
10000
10005
10010
10015
10020
10025
10030
10035
10040
10045
10050
10055
10060
10065
10070
10075
10080
10085
10090
10095
10100
10105
10110
10115
10120
10125
10130
10135
10140
10145
10150
10155
10160
10165
10170
10175
10180
10185
10190
10195
10200
10205
10210
10215
10220
10225
10230
10235
10240
102

lacquer of the invention may be pumped through a perforated extrusion die assembly as described below at a pressure of between 30 and 200 pounds per square inch. This method is to be contrasted with conventionally extruded lacquers having between 0 and 15% by weight of solvent that require a pressure in the range of between about 1000 and 5000 psi to extrude.

One suitable lacquer has the composition, by weight, of:

Component	Weight %
Organic solvent	15% - 70%
Energetic Plasticizer	0 - 40%
Stabilizer	0.1% - 2.5%
Nonenergetic Plasticizer	0 - 10%
Water	0 - 10%
Nitrocellulose	balance

In a preferred embodiment, the lacquer has the composition, by weight, of:

Component	Weight %
Ethyl Acetate	30% - 65%
Nitroglycerin	5% - 25%
Stabilizer	0.25% - 1.5%
Dibutylphthlate	0 - 3%
Water	1% - 4%
Nitrocellulose	balance

Without wishing to be bound by any particular theory, it is believed that the lacquers formed from these components function as a Newtonian shear thinning fluid. The lacquer made according to the method of the invention has a low viscosity and is easily

pumped through the extrusion die assembly and thereby requiring less energy and equipment costs.

In order to produce the perforated propellant, the lacquer is pumped through an extrusion die assembly and into an aqueous solution, referred to as liquor. The extrusion die assembly has a plurality of die holes, each of which has at least one pin tip positioned therein to produce grains having hollow cores (perforations). The liquor is preferably water-based, and generally maintained at a temperature of between about 35 and 80°C. Up to about 6% by weight of a salt (a dewatering agent) and up to about 6% by weight of a surfactant (an antiagglomerating agent) may be added to the liquor. A suitable salt is sodium sulfate, and a suitable surfactant is a colloid. Rotating knives adjacent to the base surface of the plate cut the lacquer strand into perforated cylinders of lengths which are controlled by the rate of revolution of the rotating knives and/or by controlling the pump speed. Generally, the cut perforated propellant grains have a length-to-diameter ratio of approximately 2:1. The liquor is then used to safely transport the perforated propellant through both the dewatering and solvent removal and grain hardening stages.

To control dewatering, temperature, time, residual solvent and salt concentration in the liquor are controlled. Typically dewatering involves heating the liquor to a temperature of

between about 35°C and 80°C, and preferably of between 40°C and 60°C.

After dewatering, and/or while dewatering, the perforated grains then go through a solvent removal process. This process can begin with the addition of solventless liquor to the system. This step dilutes the solvent in the liquor and results in solvent removal (leaching) from the perforated grains at a controllable rate. This method of solvent removal can be used to remove enough solvent such that the perforated grains become tough and leathery, however in some cases it may be desirable to leave up to about 40% solvent by weight in the grained material. At this stage, the perforated grains can be heated without softening to the point of deformation.

To harden the grains, the temperature of the perforated grains and liquor is increased and/or vacuum is applied until the solvent is removed to a level sufficient enough for storage. Heating may be up to any temperature up to or less than the boiling point of water, and is generally dependent on whether a vacuum is employed. At atmospheric pressure, a temperature of up to about 99°C may be utilized. At 11.5 inches of pressure, the maximum temperature is about 86°C.

The perforated grains can be further impregnated or coated, such as with nitroglycerin (an energetic plasticizer) or with a deterrent, and dried for use to form the finished propellant.

Changing the shape of the die hole of the extrusion die assembly changes the outer surface configuration of the grains and influences burn rate and performance. Exemplary shapes for propellant grains are illustrated in Figs. 1A, 1B, 2A, 2B, and

3. Fig. 1A shows a grain having a circular cross section and a perforation 40 centered in the strand cross section and running parallel to the longitudinal axis of the strand. The grain shown in Fig. 1A can be compressed to form a grain having an ellipsoidal cross section as shown in Fig. 1B. The flattened

propellant grain with ellipsoidal cross section of Fig. 1B, provides for increased packing density for increased propellant weight capability when compared to the grain with a circular cross section of Fig. 1A. The Fig. 1B shape also has utility to decrease temperature sensitivity (the tendency of a propellant to burn quicker at higher temperatures and slower at lower temperatures).

Figs. 2A and 2B show the addition of multiple perforations to influence burn characteristics of the grains. In this embodiment, the extrusion die assembly would have a plurality of pin tips to form the desired number of perforations through the strand. The configuration of Fig. 2B having an ellipsoidal cross section is made in a similar manner to the grain shown in Fig. 1B.

Fig. 3 illustrates a ridged, perforated, propellant grain with a geometry that provides for a low packing density for a lower propellant charge weight and also fills a cartridge volume, reducing ullage. The ridged propellant grains are characterized by superior ignition and flame permeability when compared to similarly configured perforated propellants without the ridges. The reduction in ullage provides enhanced safety and ballistic uniformity.

While the invention has been described in combination with embodiments thereof, it is evident that many alternatives, modifications and variations will be apparent to those skilled in the art in light of the foregoing description. Accordingly, it is intended to embrace all such alternatives, modifications and variations as fall within the spirit and broad scope of the appended claims. All patent applications, patents, and other publications cited herein are incorporated by reference in their entireties.